

Sintered Neodymium-Iron-Boron Magnets

Also available in other Energy Products from 30-55MGOe and Maximum Temperatures up to 230°C / 446°F. If you require DFAR Compliant material please contact our sales team directly with your requirements.

Characteristic		Units	min.	nominal	max.
B_r Residual Induction		Gauss	14,000	14,250	14,500
		mT	1400	1425	1450
H_{CB} Coercivity		Oersteds	10,500	12,200	13,900
		kA/m	836	971	1106
H_{cJ} Intrinsic Coercivity		Oersteds	12,000		
		kA/m	955		
BH_{max} Maximum Energy Product		MGOe	47	49	51
		kJ/m ³	374	390	406

Characteristic		Units	Nominal
Reversible Temperature Coefficients ⁽¹⁾			
of Induction, $\alpha(B_r)$		%/°C	-0.120
of Coercivity, $\alpha(H_{cJ})$		%/°C	-0.690
Curie Temperature, T_c		°C	310
Recommended Max use temperature ⁽²⁾		°C	80

Characteristic		Units	Nominal
Density		g/cm ³	7.5
Vickers Hardness		Hv	620
Coef Thermal Expansion		%/°Cx10 ⁻⁶	C // 7.5
		C ⊥	-0.1
Electrical Resistivity		μΩ • cm	180
Specific Heat		cal/g°C	0.11
		J/kg • K	460
Bending (flexural) Strength		MPa	285

Notes: (1) Coefficients measured between 20 and 80 °C

(2) Recommended maximum use temperature based on a minimum P_c of 2.2.

These magnetic characteristics and demagnetization curves represent typical production magnet performance across the specified temperature spectrum. Empirical testing for your application is advised for suitability determination.

Dura Magnetics Inc also supplies Alnico, Samarium Cobalt, and Ceramic magnets and magnetic assemblies, please contact sales@duramag.com or visit www.duramag.com.

