

Sintered Neodymium-Iron-Boron Magnets

Also available in other Energy Products from 30-55MGOe and Maximum Temperatures up to 230°C / 446°F. If you require DFAR Compliant material please contact our sales team directly with your requirements.

Magnetic Properties	Characteristic	Units	min.	nominal	max.
	B_r Residual Induction	Gauss	14,000	14,150	14,300
	mT	1400	1415	1430	
H_{cB} Coercivity	Oersteds	13,100	13,400	13,700	
	kA/m	1043	1066	1090	
H_{cJ} Intrinsic Coercivity	Oersteds	14,000			
	kA/m	1,114			
BH_{max} Maximum Energy Product	MGOe	47	48	49	
	kJ/m ³	374	382	390	

Thermal Properties	Characteristic	Units	Nominal
	Reversible Temperature Coefficients ⁽¹⁾		
of Induction, $\alpha(B_r)$	%/°C		-0.120
of Coercivity, $\alpha(H_{cJ})$	%/°C		-0.650
Curie Temperature, T_c	°C		310
Recommended Max use temperature ⁽²⁾	°C		100

Physical Properties	Characteristic	Units	Nominal
	Density	g/cm ³	
Vickers Hardness	Hv		620
Coef Thermal Expansion	% / °C x 10 ⁻⁶	C //	7.5
		C ⊥	-0.1
Electrical Resistivity	μΩ • cm		180
Specific Heat	cal/g • °C		0.11
	J/kg • K		460
Bending (flexural) Strength	MPa		285

Notes: (1) Coefficients measured between 20 and 100 °C

(2) Recommended maximum use temperature based on a minimum P_c of 2.2.

These magnetic characteristics and demagnetization curves represent typical production magnet performance across the specified temperature spectrum. Empirical testing for your application is advised for suitability determination.

Dura Magnetics Inc also supplies Alnico, Samarium Cobalt, and Ceramic magnets and magnetic assemblies, please contact sales@duramag.com or visit www.duramag.com.

